

Implications of the universal scaling relation in high-temperature superconductors

A. Rosencwaig*

ARIST, Danville, CA 94506

ABSTRACT

The recently discovered universal scaling relation between the superconducting density and the transition temperature in high-temperature superconductors appears to indicate that those normal state carriers that are undergoing a superconducting transition at $T \cong T_c$, are experiencing critical dissipation and acting as preformed pairs.

PACS Numbers: 74.20.-z, 74.20.Mn, 73.50.Gr

* Electronic mail address: allan4arist@aol.com.

Recently, Homes *et al* have reported that a simple scaling relation between the superconducting transition temperature and the superfluid density universally holds for all high-temperature superconductors, regardless of doping level, crystal structure and type of disorder, nature of dopant and direction.¹ Using a dimensional analysis, Zaanen has proposed that this scaling relation implies that the normal states in the high-temperature superconductors are extremely, or even critically, dissipative.² The Homes relation is given by,

$$\rho_s = \eta \sigma_{dc} T_c \quad (1)$$

where ρ_s is the superfluid density and σ_{dc} is the dc conductivity at a temperature $T \cong T_c$, where T_c is the transition temperature. Homes *et al* have determined that $\eta = 120 \pm 25 \text{ } \Omega \text{cm}^{-1} \text{K}^{-1}$ when ρ_s is in cm^{-2} and σ_{dc} is in $\Omega^{-1} \text{cm}^{-1}$.

Now,

$$\rho_s = \frac{c^2}{\lambda^2} = \frac{4\pi e^2 n_s}{m_s} \quad (2)$$

where c is the velocity of light, λ is the penetration depth and m_s , n_s and e are the mass (or effective mass), the density and the charge, respectively, of the carriers in the superconducting state at $T = 0$. The normal state dc conductivity in the CuO_2 planes, where coherent transport governed by scattering physics applies, is given by,

$$\sigma_{dc} = \frac{ne^2 \tau}{m} = \frac{ne^2 \Lambda}{m v} \quad (3)$$

where n is the carrier density, τ is the relaxation time, m is the carrier effective mass, Λ is the carrier mean free path or scattering length and v is the average carrier velocity. At $T \cong T_c$, the normal conductivity has already significantly increased and thus is dominated by those carriers (density $n' \leq n$) that are undergoing the superconducting transition. Thus $n' = n_s$. Since n' can be $< n$, this is consistent with Tanner's rule³ which states that in high- T_c cuprates n_s tends to be $\approx 1/4 n$. Thus,

$$\sigma_{dc}(T \approx T_c) = \frac{n' e^2 \Lambda}{m' v} = \frac{n_s e^2 \Lambda}{m' v} \quad (4)$$

where m' is the effective mass of those normal state carriers that are undergoing a superconducting transition at $T \cong T_c$.

But,

$$m'v = \frac{2\pi\hbar}{\lambda_T} \quad (5)$$

where \hbar is the Planck constant and λ_T is the de Broglie thermal wavelength for the quasiparticles that are undergoing the superconducting transition at $T \cong T_c$. Therefore, substituting both Eqn. (5), and n_s from Eqn. (4), into Eqn. (1), we get,

$$\rho_s = \frac{8\pi^2\hbar}{m'\Lambda\lambda_T} \sigma_{dc} = \frac{8\pi^2\hbar}{m_s\lambda_T^2} \left(\frac{\lambda_T}{\Lambda} \right) \sigma_{dc} \quad (6)$$

But,

$$\lambda_T^2 = \frac{2\pi\hbar^2}{m'kT_c} \quad (7)$$

where k is the Boltzmann constant. Thus,

$$\rho_s = \frac{4\pi k}{\hbar} \left(\frac{\lambda_T}{\Lambda} \right) \left(\frac{m'}{m_s} \right) \sigma_{dc} T_c \quad (8)$$

The proportionality factor η in Eqn. (1) is then,

$$\eta = \frac{4\pi k}{\hbar} \left(\frac{\lambda_T}{\Lambda} \right) \left(\frac{m'}{m_s} \right) \quad (9)$$

This is the expression for η when ρ_s is in units of s^{-2} and σ_{dc} is in units of s^{-1} giving units of η in $s^{-1}K^{-1}$. To compare theory with experiment, we must set ρ_s and σ_{dc} to be in units of cm^{-2} and $\Omega^{-1}cm^{-1}$ respectively. To do this, we divide the right-hand side of Eqn. (9) by c^2 and the left-hand side by Ωc , which results in,

$$\begin{aligned} \eta &= \frac{4\pi k}{\hbar c} \left(\frac{\lambda_T}{\Lambda} \right) \left(\frac{m'}{m_s} \right) \\ &= 55 \left(\frac{\lambda_T}{\Lambda} \right) \left(\frac{m'}{m_s} \right) \Omega cm^{-1} K^{-1} \end{aligned} \quad (10)$$

Since the experimental value for η is $120 \pm 25 \text{ } \Omega \text{ cm}^{-1} \text{ K}^{-1}$,¹

$$\left(\frac{\lambda_T}{\Lambda} \right) \left(\frac{m'}{m_s} \right) \approx 2 \quad (11)$$

One way for Eqn. (12) to be true is if both $\Lambda \approx \lambda_T$ and $m' \approx 2m_s$. The first condition is similar to Zaanen's suggestion that the normal carriers at $T \cong T_c$ undergo critical dissipation,² although here this condition may be limited to only those normal carriers that are undergoing the superconducting transition at $T \cong T_c$. The second condition implies that the normal carriers undergoing the superconducting transition at $T \cong T_c$ are acting as preformed pairs. Again, this does not necessarily mean that all the normal carriers are preformed pairs, only that those carriers undergoing the superconducting transition at $T \cong T_c$ act as preformed pairs.

The fact that the Homes relation also holds for the c-axis as well is surprising given that the normal state transport in this direction is generally governed by hopping rather than scattering physics. A possible explanation may be that at $T \cong T_c$ preformed pairs begin to form along the c-axis and that these preformed pairs undergo coherent transport along the c-axis that is governed by scattering physics, albeit with critical dissipation with appropriately larger effective mass m' and smaller thermal wavelength λ_T and scattering length Λ .

ACKNOWLEDGMENTS

I would like to acknowledge helpful discussions with M. Greven and C.C. Homes.

REFERENCES

1. C.C. Homes, S.V. Dordevic, M. Strongin, D.A. Bonn, Ruixing Liang, W.N. Hardy, Seiki Koymia, Yoichi Ando, G. Yu, N. Kaneko, X. Zhao, M. Greven, D.N. Basov, T. Timusk, *Nature* **430**, 539 (2004).
2. Jan Zaanen, *Nature* **430**, 512 (2004).
3. D.B. Tanner, H.L. Liu, M.A. Quijada, A. Zibold, H. Berger, R.J. Kelley, M. Onellian, F.C. Chou, D.C. Johnston, J.P. Rice, D.M. Ginsberg, J.T. Markert, *Physica B* 244, 1 (1998).