

Table I. Refined parameters for $\text{La}_{0.7}\text{Sr}_{0.3}\text{Mn}_{1-x}\text{Cu}_x\text{O}_3$, $R\bar{3}c$ space-group, at room temperature and $T=10\text{K}$. Numbers in parentheses are statistical errors. a and c are the lattice parameters. m is magnetic moment. V is the unit cell volume. χ^2 is $[\text{R}_{wp}/\text{R}_{exp}]^2$ where R_{wp} is the residual error of the weighted profile. The magnetic moments of the $x \geq 0.15$ samples at RT are not refined. Electronic bandwidth parameter $W'=10^* \cos\omega / (d_{Mn-O})^{3.5}$ (arb. unit).

Composition (x)	0.00	0.05	0.10	0.15	0.20
T=300K					
a (\AA)	5.5038(2)	5.5003(2)	5.4987(2)	5.4982(2)	5.4941(2)
c (\AA)	13.3552(5)	13.3387(4)	13.3341(5)	13.3304(6)	13.3180(6)
V (\AA^3)	350.351(18)	349.473(17)	349.153(18)	348.990(22)	348.152(24)
m (μ_B)	2.512(28)	1.975(30)	1.411(101)	-	-
χ^2 (%)	2.81	2.69	2.91	4.89	5.36
W'	0.953	0.956	0.958	0.959	0.961
T=10K					
a (\AA)	5.4812(1)	5.4845(1)	5.4823(1)	5.4858(1)	5.4855(2)
c (\AA)	13.2759(3)	13.2797(4)	13.2737(4)	13.2718(4)	13.2637(4)
V (\AA^3)	345.415(13)	345.931(16)	345.504(17)	345.897(17)	345.642(17)
m (μ_B)	3.445(24)	3.327(27)	3.160	2.272(50)	0.727(93)
χ^2 (%)	3.18	2.76	3.30	2.67	2.82
W'	0.967	0.968	0.969	0.966	0.966