

TABLE I: Refined parameters for $\text{La}_{0.7}\text{Sr}_{0.3}\text{Mn}_{1-x}\text{Ti}_x\text{O}_3$ compound with $R\bar{3}c$ space-group at room temperature($T=300\text{K}$). Numbers in parentheses are statistical errors. a and c are the lattice parameters. m is magnetic moment. V is the unit cell volume. B is the isotropic temperature parameter. χ^2 is $[\text{R}_{wp}/\text{R}_{exp}]^2$ where R_{wp} is the residual error of the weighted profile.

Composition	0.00	0.03	0.05	0.10	0.15	0.20
a (\AA)	5.5038(2)	5.5107(1)	5.5157(2)	5.5225(2)	5.5306(2)	5.5310(2)
c (\AA)	13.3553(5)	13.3635(4)	13.3699(5)	13.3845(5)	13.4032(6)	13.4124(6)
V (\AA^3)	350.364(18)	351.445(16)	352.261(18)	353.508(21)	355.042(22)	355.341(23)
m (μ_B)	2.514(28)	2.121(33)	1.022(63)	0.0	0.0	0.0
χ^2 (%)	2.81	3.28	3.60	3.23	4.64	2.98
O, 18e,x	0.5422(2)	0.5437(2)	0.5448(2)	0.5460(2)	0.5469(2)	0.5461(2)
B(\AA^2), La(Sr),6a	0.882(33)	0.8124(33)	0.873(35)	1.030(42)	0.975(43)	1.149(40)
B(\AA^2), Mn(Ti),6b	0.423(54)	0.556(56)	0.574(59)	0.364(66)	0.394(67)	0.404(63)
B(\AA^2), O,18e	1.221(25)	1.248(25)	1.306(27)	1.501(37)	1.475(37)	1.586(35)