

TABLE II: Refined parameters for  $\text{La}_{0.7}\text{Sr}_{0.3}\text{Mn}_{1-x}\text{Ti}_x\text{O}_3$  compound with  $R\bar{3}c$  space-group at low temperature( $T=10\text{K}$ ). Numbers in parentheses are statistical errors.  $a$  and  $c$  are the lattice parameters.  $m$  is magnetic moment.  $V$  is the unit cell volume.  $B$  is the isotropic temperature parameter.  $\chi^2$  is  $[\text{R}_{wp}/\text{R}_{exp}]^2$  where  $\text{R}_{wp}$  is the residual error of the weighted profile.

Composition	0.00	0.03	0.05	0.10	0.15	0.20
$a$ ( $\text{\AA}$ )	5.4811(1)	5.4940(1)	5.4989(1)	5.5116(1)	5.5089(2)	5.5053(3)
$c$ ( $\text{\AA}$ )	13.2756(3)	13.3037(4)	13.3137(4)	13.3354(4)	13.3421(6)	13.3746(10)
$V$ ( $\text{\AA}^3$ )	345.397(13)	347.756(14)	348.644(16)	350.820(15)	350.652(22)	351.056(35)
$m$ ( $\mu_B$ )	3.443(25)	3.461(27)	3.506(32)	3.422(28)	3.282(36)	2.913(51)
$\chi^2$ (%)	3.23	3.51	2.89	2.69	3.72	4.90
O, 18e,x	0.5431(1)	0.5442(2)	0.5448(1)	0.5467(1)	0.5469(2)	0.5472(2)
B( $\text{\AA}^2$ ), La(Sr),6a	0.167(26)	0.240(28)	0.302(33)	0.318(28)	0.449(37)	0.269(48)
B( $\text{\AA}^2$ ), Mn(Ti),6b	0.127(45)	0.230(49)	0.271(57)	0.169(47)	0.291(62)	0.174(81)
B( $\text{\AA}^2$ ), O,18e	0.328(21)	0.536(23)	0.595(27)	0.649(22)	0.926(28)	0.945(36)