

May 19, 1978

Mr. H. M. Pauley, Purchasing Manager - Commodities and Chemicals

T. P. Pettigrew, Manufacturing Services Manager - Research and Development

Activated Carbon

We are listing below the results of our Carbon tetrachloride activity determinations on samples of activated carbon taken from shipments received at Hanmer Division from March 1 through May 10:

<u>Supplier</u>	<u>Date Received</u>	<u>CCl₄ Activity, %</u>
Witco	3-1-78	55.8
Witco	3-17-78	60.6
Witco	3-24-78	57.8
Witco	4-7-78	54.0
Witco	4-26-78	55.0
Witco	5-5-78	53.0
Witco	5-10-78	59.5
Westvaco	3-2-78	59.3
Westvaco	3-16-78	55.3
Westvaco	3-22-78	53.6
Westvaco	3-29-78	56.6
Westvaco	4-4-78	54.5
Pittsburgh	3-9-78	63.1
Pittsburgh	3-20-78	64.4
Pittsburgh	3-29-78	62.3
Pittsburgh	3-31-78	64.5

Avg. 56.5
Avg. 55.9
Avg. 63.8

Our acceptable CCl₄ activity range is 57 to 75 percent. Please contact Witco and Westvaco concerning low values obtained on material they are currently supplying. The material from Pittsburgh is well within our acceptable range.



DRB/ro

cc: Mr. R. J. Smith, Manager - Hanmer Division

bc: RSS:PHL
TPP:PRC
DRB